

SEFA 8.0 CABINET SURFACE FINISH TESTS

Performed for: TIGER Drylac U.S.A., Inc.
3945 Swenson Avenue
St. Charles, IL 60174

Sample Description:

- Substrate Coated: Cold Rolled Steel
- Type of Coating: TIGER Epoxy Powder Coating
- Coating ID#: SEFA 8M 69 Series Glossy

Reference: Scientific Equipment & Furniture Association (SEFA)
Laboratory Furniture Casework, Shelving and Tables Recommended Practices
SEFA 8 M-2016

Section 8.0 Cabinet Surface Finish Test Results:

8.1 Chemical Spot Test
See detailed results on attached form.

Four Level 3 conditions permitted Rating: ☒ Pass ☐ Fail

There are (4) Level 3 conditions evident

8.2 Hot Water Test Rating: ☒ Pass ☐ Fail

There is no visible effect due to the hot water (1000 ml @ 94 C for 5 min.)

8.3 Finish Impact Test Rating: ☒ Pass ☐ Fail

There are no checks or cracks evident due to impact

8.4 Paint Adhesion on Steel Rating: ☒ Pass ☐ Fail

100% of the grid areas remain intact upon completion of the test.

8.5 Paint Hardness on Steel Rating: ☒ Pass ☐ Fail

The paint finish did withstand the abrasion of a 4H pencil in attempting to penetrate through to the substrate

COMPANY INFORMATION	TEST SUPERVISOR INFORMATION
Name: Cardinal Environmental, Inc.	Name: Arthur F. Lautenbach
Address: 3303 Paine Avenue	Title: Environmental Analyst
Sheboygan, WI 53081	Signature: <i>Arthur F. Lautenbach</i>
Telephone: (920) 459-2500	COMPANY OFFICER INFORMATION
Fax: (920) 459-2503	Name: Scott Hanson
	Title: President
Date: 3/26/2020	Signature: <i>Scott O. Hanson</i>

