

DALLAS LABORATORIES, INC.

CONSULTANTS AND TECHNOLOGISTS
ANALYTICAL AND RESEARCH CHEMISTS —
CHEMICAL ENGINEERS — PETROLEUM ENGINEERS

MEMBERS

AMERICAN INSTITUTE OF CHEMICAL ENGINEERS
NATIONAL SOCIETY OF PROFESSIONAL ENGINEERS
TEXAS SOCIETY OF PROFESSIONAL ENGINEERS
ASM INTERNATIONAL
SOCIETY OF PETROLEUM ENGINEERS OF AIME

P. O. BOX 152837
1323 WALL ST.

DALLAS, TEXAS 75315

MEMBERS

AMERICAN CHEMICAL SOCIETY
AMERICAN SOCIETY FOR TESTING MATERIAL
AMERICAN NATIONAL STANDARDS INSTITUTE
AMERICAN SOCIETY FOR QUALITY CONTROL

Submitted by: TIGER Drylac U.S.A., Inc.
1100 Commons Blvd.
Reading, PA 19610

Date: April 12, 2007

Attn: Burkhard Maier

Report No.: 38407-4

REPORT

Sample:

Coated aluminum panels
Paint: Series 029 MATT Metallic
Production Date: Unknown
Cure: Unknown
Pre-treatment: Unknown
Drawing: N/A

A. Procedure

Submitted sample was tested for **informational purposes** according to AAMA 2603-02 "Voluntary Specification Performance Requirements and Test Procedures for Pigmented Organic Coatings on Aluminum Extrusions and Panels", Sections 6.1 through 6.7.2, with the following results:

B. Results

| <u>Test</u> | <u>Results</u> | <u>AAMA 2603-02 Specification Requirements</u> |
|-----------------------|----------------|--|
| 6.1 Color Uniformity | Standard | Standard |
| 6.2 Specular Gloss | 31.3 | As Reported |
| 6.3 Dry Film Hardness | Pass H | H Hardness and No Film Rupture |
| 6.4 Film Adhesion | | |
| 6.4.1.1 Dry | Pass | No Loss of Adhesion |
| 6.4.1.2 Wet | Pass | No Loss of Adhesion |


| <u>Test</u> | <u>Results</u> | <u>AAMA 2603-02 Specification Requirements</u> |
|--------------------------|-----------------------|--|
| 6.5 Impact Resistance | Pass | No Removal of Film from Substrate |
| 6.6 Chemical Resistance | | |
| 6.6.1 Muriatic Acid | Pass | No Blistering or Visible Change |
| 6.6.2 Mortar | Pass | No Blistering or Visible Change |
| 6.6.3 Detergent | Pass | No Film Adhesion Loss or Visible Change |
| 6.7 Corrosion Resistance | | |
| 6.7.1 Humidity | Pass (No blisters) | Not Greater Than Few #8 Blisters. |
| 6.7.2 Salt Spray | Pass | |
| Scribe | 10 | 7 Minimum Rating |
| Field | 10 | 8 Minimum Rating |

Date Testing Started: 1-10-07
 Date Testing Completed: 4-12-07
 Date Test Report Expires: N/A (Informational)
 Sampled by: N/A

Testing Conducted At: Dallas Laboratories, Inc., 1323 Wall Street, Dallas, Texas 75215.

Test results indicate that the sample tested is in compliance with all of the performance requirements of AAMA 2603-02 for Pigmented Organic Coatings on Aluminum Extrusions and Panels, except for Section 6.8.1 Outdoor Exposure which must be furnished by the coating supplier for full compliance to AAMA 2603 as specified by AAMA.

DALLAS LABORATORIES, INC.



 Kevan W. Jones, Vice President

Analyst: GF
 KWJ:td