

TIGITAL® Melamine-Primer Series 145/0

Properties

Serie 145/00002

| Viscosity | 24 – 28 mPas 9 – 11 mPas |
|--|-----------------------------|
| UV dose in the case of hardening with a UV-LED lamp 395 mm | 750 mJ/cm ² |

Serie 145/00003

| Viscosity | | 24 – 28 mPas 9 – 11 mPas |
|--|-------|-------------------------------|
| Surface tension | 25 °C | 22 – 26 dyn/cm |
| UV dose in the case of hardening with a UV-LED lamp 395 mm | | 800 – 1200 mJ/cm ² |

Versions

- Series 145/00002 UV-hardening
- Series 145/00003 UV-LED-hardening

Shelf life

9 months for storage between 15 and 35°C.

Package sizes

- 1 I PE bottles (black)
- 5 I PE containers (black)
- Other package sizes are available on request.

Recommended cleaning and flushing fluid

TIGER Flush 151/00001

Applications

The TIGER Melamine-Primer is a UV-LED thermosetting inkjet ink on acrylate base which achieves excellent adhesion properties on varying rigid substrates, such as melamine resin, glas or on various metal surfaces.

After hardening the printed primer layer can be overprinted with pigmented inkjet ink, such as e.g. series 135 - UV Universal Ink (with an excellent adhesion of the interim layer).

Printing conditions

The inks can be processed at up to 55 °C. The necessary UV dose is oriented according to the printed coating thickness, whereby the previously specified $800-1200~\text{mJ/cm}^2$ of the radiation dose correspond to the typical radiation dose of a UV-LED lamp of with a ink coating thickness of $10-15~\mu\text{m}$ (e.g. for printing components).

Compatibility of materials

Compatible materials:

- PF
- PE (HD + LD)
- Stainless steel
- PTFE
- EPDM rubber

Incompatible materials:

- PVC
- Butyl rubber
- Brass
- Viton®
- Nitrile plastics
- Polyurethane rubber
- Neoprene



Disclaimer

Our verbal and written recommendations for the use of our products are based upon experience and in accordance with present technological standards. These are given in order to support the buyer or user. They are non-committal and do not create any additional commitments to the purchase agreement. They do not release the buyer from verifying the suitability of our products for the intended application. We warrant that our products are free of flaws and defects to the extent as stipulated in our Terms of Delivery and Payment.

As part of our duty to inform, we modify our product information periodically according to technical progress. As such, the most recently valid version of this information applies and is available at any time from the download area at www.tiger-coatings.com. TIGER Coatings GmbH & Co. KG reserves the right to make changes to the product data sheet without written notification.

This product sheet replaces all previous ones about this topic and only represents a product overview. In case of use of a product outside of our standard product line according to the standard product list (last valid version), the corresponding product data sheet must be requested. Our technical notes and the general Terms of Delivery and Payment, the most recent version of which you can call up at any time at www.tiger-coatings.com in the download area, are an integral component of this data sheet.

> certified according to EN ISO 9001 / 14001



TIGER Coatings GmbH & Co. KG

Negrellistraße 36, 4600 Wels, Austria

Т +43 / (0)7242 / 400-0

F +43 / (0)7242 / 650 08

powdercoatings@tiger-coatings.com

www.tiger-coatings.com