

# SERIES 250/00113 wheel line

typical application	automotive
chemistry	acrylic (GMA)
surface	smooth
gloss	>100 - according to ISO 2813 at 20° angle
recommended film thickness	2.5-3.5 mils (60-80 µm) - according to EN ISO 2360
recommended cure parameters	20 minutes at 347 °F (175 °C) substrate temperature
application type	electrostatic spray
specific gravity	1.15±0.03 g/ml
storage stability	3 months at no more than 59-68 °F (15-20 °C)

## Test results

The film properties were determined on aluminum test panels with chromate-free conversion.

test method	test	test result
ISO 2409	<b>cross cut</b>	value 0
EN ISO 20567-1 method B	<b>determination of stone-chip resistance</b> (multi-impact test)	value 1-2
EN ISO 11341 method 1	<b>weathering in humid-warm climate</b> 3,200 hours	ISO 2813 at 60° angle gloss retention >80%

test method	test	test result	
EN ISO 6270-2-CH	<b>condensation atmosphere with constant humidity</b> 240 hours	degree of blistering - EN 4628-2 degree of rusting - EN 4628-3	0 (S0) Ri 0
EN ISO 9227	<b>copper-accelerated acid salt spray test (CASS)</b> 240 hours	corrosion - EN 4628-8 delamination - EN 4628-8 degree of blistering - EN 4628-2 degree of rusting - EN 4628-3	c ≤5/64 inches (2 mm) d ≤5/64 inches (2 mm) 0 (S0) Ri 0
VDA 621-415	<b>cyclic corrosion test</b> 10 cycles	corrosion - EN 4628-8 delamination - EN 4628-8 degree of blistering - EN 4628-2 degree of rusting - EN 4628-3	c ≤5/64 inches (2 mm) d ≤5/64 inches (2 mm) 0 (S0) Ri 0

## Disclaimer

TIGER's verbal and written recommendations for the use of its products are based upon experience and in accordance with current technological standards. These are provided in order to support the buyer or user. They are non-committal and do not create any additional commitments to the purchase agreement. They do not release the buyer from verifying the suitability of TIGER products for the intended application. TIGER warrants that its products are free of flaws and defects to the extent stipulated in the Terms of Delivery and Payment.

As part of TIGER product information program, each Product Data Sheet is updated periodically. The latest version shall prevail. It is recommended to always check for the latest editions on TIGER's website download area [www.tiger-coatings.com](http://www.tiger-coatings.com) to make sure you have the most current version of this Product Data Sheet. The information on TIGER's Product Data Sheets are subject to change without notification.

This Product Data Sheet supersedes and replaces all previous Product Data Sheet versions and notes to customers published in relation to this product and is only intended to provide a general overview on the product.

Latest versions of Technical Information Sheets and Terms of Delivery and Payment are downloadable from [www.tiger-coatings.com](http://www.tiger-coatings.com) and form an integral part of this Product Data Sheet.

Certified according to  
ISO 9001 | 14001

**TIGER Drylac Canada Inc.**  
110 Southgate Drive  
Guelph, ON N1G 4P5 | Canada  
**T** 1 800 243 8148  
**F** 1 877 926 8148  
**E** [office.ca@tiger-coatings.com](mailto:office.ca@tiger-coatings.com)  
**W** [www.tiger-coatings.com](http://www.tiger-coatings.com)